

2022 Tekstil info		7+7 FUTON ApS	Gram	Martindale	Oeko-Tex	Fastness to Light	Fastness to rubbing
INNOVATION LIVING	Materiale		pr.m2		Certified	Tested by ISO 105-B02	Tested by ISO 105-X12
Dess.216 Flashtex, Mørkegrå	100% Polyester		295	116000	Yes	Fastness to Light 4-5	Fastness to rubbing 4
Dess.217 Flashtex, Lysegrå	100% Polyester		295	116000	Yes	Fastness to Light 4-5	Fastness to rubbing 4
Dess.316 Cordufine, Pine Green	85% Polyester / 15% Polyamide		400	100000	Yes	Fastness to Light 5	Fastness to rubbing 5
Dess.317 Cordufine, Rust	85% Polyester / 15% Polyamide		400	100000	Yes	Fastness to Light 5	Fastness to rubbing 5
Dess.318 Cordufine, Beige	85% Polyester / 15% Polyamide		400	100000	Yes	Fastness to Light 5	Fastness to rubbing 5
Dess.461 Læder look, Vintage	85% Polyvinyl chloride (PVC) / 15% Viscose		530	400000	No	Fastness to Light 4-5	Fastness to rubbing 4-5
Dess.507 Elegance, Brændt Karry	100% Polyester		380	60000	Yes	Fastness to Light 4-5	Fastness to rubbing 4-5
Dess.515 Nist, Blå	96% Polyester / 4% Linen~hør		390	141500	Yes	Fastness to Light 4-5	Fastness to rubbing 5
Dess.518 Elegance, Grøn	100% Polyester		380	60000	Yes	Fastness to Light 4-5	Fastness to rubbing 4-5
Dess.521 Mixed Dance, Grå	100% Polyester		375	85500	No	Fastness to Light 4-5	Fastness to rubbing 5
Dess.525 Mixed Dance, Lyseblå	100% Polyester		375	85500	No	Fastness to Light 4-5	Fastness to rubbing 5
Dess.527 Mixed Dance, Natural	100% Polyester		375	85500	No	Fastness to Light 4-5	Fastness to rubbing 5
Dess.528 Mixed Dance, Blå	100% Polyester		375	85500	No	Fastness to Light 4-5	Fastness to rubbing 5
Dess.531 Off White, Bouclé	100% Polyester		430	27000	No	Fastness to Light 5	Fastness to rubbing 4-5
Dess.533 Bouclé, Ash Grey	100% Polyester		430	27000	No	Fastness to Light 5	Fastness to rubbing 4-5
Dess.534 Bouclé, Black Raven	100% Polyester		430	27000	No	Fastness to Light 5	Fastness to rubbing 4-5
Dess.550 Fanual, sort	80% Polyester_17,5% Lether_2,5% Polyurethane		335	56000	No	Fastness to Light 4-5	Fastness to rubbing 4
Dess.551 Faulan, Brun	80% Polyester_17,5% Lether_2,5% Polyurethane		335	56000	No	Fastness to Light 4-5	Fastness to rubbing 4
Dess.552 Soft, Pacific Pearl	100% Polyester		460	100000	Yes	Fastness to Light 4-5	Fastness to rubbing 5
Dess.554 Soft, Senneps blomst	100% Polyester		460	100000	Yes	Fastness to Light 4-5	Fastness to rubbing 5
Dess.558 Soft, Indigo	100% Polyester		460	100000	Yes	Fastness to Light 4-5	Fastness to rubbing 5
Dess.563 Twist, Trækul	100% Polyester		400	36000	No	Fastness to Light 4-5	Fastness to rubbing 5
Dess.565 Twist, Granite	100% Polyester		400	36000	No	Fastness to Light 4-5	Fastness to rubbing 5
Dess.571 Vivus, Dusty Sand	100% Recycled Polyester		400	78000	Yes	Fastness to Light 4-5	Fastness to rubbing 4-5
Dess.573 Vivus, Dusty Blue	100% Recycled Polyester		400	78000	Yes	Fastness to Light 4-5	Fastness to rubbing 4-5
Dess.574 Vivus, Dusty Off White	100% Recycled Polyester		400	78000	Yes	Fastness to Light 4-5	Fastness to rubbing 4-5
Dess.575 Vivus, Dusty Olive	100% Recycled Polyester		400	78000	Yes	Fastness to Light 4-5	Fastness to rubbing 4-5
Dess.577 Kenya, mørke grå	100% Polyester		550	119000	No	Fastness to Light 5	Fastness to rubbing 4-5
Dess.578 Kenya, Taupe	100% Polyester		550	119000	No	Fastness to Light 5	Fastness to rubbing 4-5
Dess.579 Kenya, Grus	100% Polyester		550	119000	No	Fastness to Light 5	Fastness to rubbing 4-5
Dess.580 Argus, Navy Blue	100% Recycled Polyester		515	67000	No	Fastness to Light 4-5	Fastness to rubbing 4
Dess.581 Argus, Rust	100% Recycled Polyester		515	67000	No	Fastness to Light 4-5	Fastness to rubbing 4
Dess.583 Argus, Grey	100% Recycled Polyester		515	67000	No	Fastness to Light 4-5	Fastness to rubbing 4
Dess.584 Argus, Natural	100% Recycled Polyester		515	67000	No	Fastness to Light 4-5	Fastness to rubbing 4
Dess.585 Argus, Brown	100% Recycled Polyester		515	67000	No	Fastness to Light 4-5	Fastness to rubbing 4
Dess.586 Phobos, Latte	100% Polyester		530	100000	No	Fastness to Light 5	Fastness to rubbing 4-5
Dess.587 Phobos, Mocha	100% Polyester		530	100000	No	Fastness to Light 5	Fastness to rubbing 4-5
Dess.590 Micro Check, Grå	100% Polyester		320	27000	No	Fastness to Light 5	Fastness to rubbing 4-5
Dess.595 Corduroy	90% Polyester_10% Nylon		370	109000	Yes	Fastness to Light 5	Fastness to rubbing 4
Dess.612 Blida, Sandgrå	80% Polyester / 20% Linen~hør		500	200000	No	Fastness to Light 4-5	Fastness to rubbing 4-5